

**THE FOLLOWING ARE THE ENGLISH TRANSLATION
OF ANNEXES TO THE INTERNATIONAL PRELIMINARY
EXAMINATION REPORT (ARTICLE 34):**

Amended Sheets (Pages 15 & 16)



"as enclosed to IPRP"

What is claimed is:

5

1. A solid, water-free and alkanol-free composite material comprising organic and/or inorganic water-insoluble particles or pigments in a mixture with at least one compound of the general formula (I)

10



where

R is H, C₁₋₆ alkyl or benzyl

15

A is ethyleneoxy

B is C₃₋₁₀ alkyleneoxy or mixtures thereof,

20

it being possible for groups A and B to be randomly distributed, alternating or in the form of two or more blocks in any order,

n is an integer in the range from 4 to 8

25

x is a number in the range from 1 to 25

y is a number in the range from 0 to 10

and x + y is at least 1,

30

wherein the alkoxylation and any subsequent purification of the alkoxylation product are conducted in such a way that the alkoxylates are alkanol-free.

35

2. The composite material according to claim 1, wherein the particles are present in an amount in the range from 85 to 99.9% by weight and the compounds of the general formula (I) in an amount in the range from 0.1 to 15% by weight, based on the total amount of the composite material.

3. The composite material according to claim 1 or 2, wherein the compound of the general formula (I) is an alkyl glycol alkoxylate or alkyl diglycol alkoxylate obtainable by alkoxylating C₄₋₈ alkyl glycols or diglycols with the parent alkylene oxides of the units A and/or B.
5
4. The composite material according to any one of claims 1 to 3, wherein the compound of the general formula (I) is preparable by DMC-catalyzed alkoxylation.
- 10 5. A process for producing a composite material according to any of claims 1 to 4 by mixing the organic and/or inorganic water-insoluble particles or pigments and the compounds of the general formula (I) with heating where appropriate.
- 15 6. The use of a composite material according to any one of claims 1 to 4 as a filler and/or dye and/or for preparing aqueous dispersions.
- 20 7. The use of a composite material according to any one of claims 1 to 4 for producing paper, paints, inks, coatings, formulations for mineral processing or paper finishing.
- 25 8. A paint, ink formulation, coating or overcoating composition or formulation for mineral processing, papermaking or paper finishing, comprising a composite material according to any one of claims 1 to 4 and, if appropriate, surfactants which in solution in water at 5 g/l exhibit an interfacial tension of less than 45 mN/m at 20°C, polymers if appropriate and, if appropriate, customary auxiliaries.
- 30 9. The use of compounds of the general formula (I) as defined in claim 1, 3 or 4 to treat organic or inorganic water-soluble particles or pigments for increasing wettability with polar liquids.